




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : H01M 4/92, 8/10		A1	(11) International Publication Number: WO 97/21256
			(43) International Publication Date: 12 June 1997 (12.06.97)
(21) International Application Number: PCT/US96/19731		(74) Agent: HARRIS, Scott, C.; Fish & Richardson P.C., Suite 1400, 4225 Executive Square, La Jolla, CA 92037 (US).	
(22) International Filing Date: 9 December 1996 (09.12.96)		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(30) Priority Data: 08/569,452 8 December 1995 (08.12.95) US			
(71) Applicant (for all designated States except US): CALIFORNIA INSTITUTE OF TECHNOLOGY [US/US]; 1201 East Cal- ifornia Boulevard, Pasadena, CA 91125 (US).			
(72) Inventors; and			
(75) Inventors/Applicants (for US only): SURAMPUDI, Subbarao [IN/US]; 1210 East Leadora Avenue, Glendora, CA 91741 (US). FRANK, Harvey, A. [US/US]; 5328 Newcastle Avenue #33, Encino, CA 91316 (US). NARAYANAN, Sekharipuram, R. [IN/US]; 212 East Wapello Street, Altadena, CA 91001 (US). CHUN, William [US/US]; 2206 Oros Street, Los Angeles, CA 90031 (US). JEFFRIES- NAKAMURA, Barbara [US/US]; 1420 Mirasol Drive, San Marino, CA 91108 (US). KINDLER, Andrew [US/US]; 616 Plymouth Road, San Marino, CA 91108 (US). HALPERT, Gerald [US/US]; 1000 East California Boulevard #304, Pasadena, CA 91106 (US).			
Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.			

(54) Title: DIRECT METHANOL FEED FUEL CELL AND SYSTEM



(57) Abstract

Improvements to non-acid fuel methanol fuel cells (10) include new formulations for the materials used therein. The anode (14) includes platinum and rhenium uniformly mixed together. Other materials may be substituted for these metals. The cathode (16) is made of platinum particles, and is bonded to a side of the solid polymer electrolyte membrane (18). The backing material for the fuel electrode is treated to improve its characteristics. An extremely porous electrode made by sputtering is also disclosed.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

DIRECT METHANOL FEED FUEL CELL AND SYSTEM

5 This is a continuation-in-part of 08/478,001, filed
June 7, 1995, which is a continuation of 08/135,007, filed
October 12, 1993.

Field of the Invention

 The present invention relates to direct feed
10 methanol fuel cell improvements for a system that operates
without an acid electrolyte or a reformer.

Background and Summary

 Transportation vehicles which operate on gasoline-
powered internal combustion engines have been the source of
15 many environmental problems. The output products of
internal combustion engines cause, for example, smog and
other exhaust gas-related problems. Various pollution
control measures minimize the amount of certain undesired
exhaust gas components. The process of burning, however,
20 inherently produces some exhaust gases.

 Even if the exhaust gases could be made totally
benign, however, the gasoline based internal combustion
engine still relies on non-renewable fossil fuels.

Many groups have searched for an adequate solution to the energy problems.

One possible solution has been fuel cells. Fuel cells chemically react using energy from a renewable fuel material. Methanol, for example, is a completely renewable resource. Moreover, fuel cells use an oxidation/reduction reaction instead of a burning reaction. The end products from the fuel cell reaction are typically mostly carbon dioxide and water.

Some previous methanol fuel cells used a "reformer" to convert the methanol to H_2 gas for a fuel cell. Methanol fuel cells used a strong acid electrolyte. The present inventors first proposed techniques which would allow a fuel cell to operate directly from methanol and without an acid electrolyte -- a direct feed fuel cell. The subject matter of this improvement is described in our U.S. Patent No.

_____, the disclosure of which is herewith incorporated by reference to the extent necessary for proper understanding. Since this is the work of the present inventors, of course, there is no admission made here that this patent constitutes prior art against the present invention.

The subject matter of the present invention describes further refinements of such a direct fed fuel

cell. Various improvements to the fuel cell structure itself are described herein, based on the inventors' further work on this concept. These improvements include improved formulations for the electrode which improve its operation.

5 The electrode operation includes an improved catalyst, which improves the efficiency of methanol production. Fuel cells use an expensive platinum catalyst. The electrode formulations given herein define techniques which reduce or obviate the need for the platinum catalyst.

10 Techniques for forming the cathode electrode are also described herein. These techniques optimize the operation of the cathode for use with non-pressurized air. This even further improves the efficiency of the fuel cell by allowing ambient temperature and atmospheric pressure air
15 as the reduction mechanism.

 Formation techniques for the electrodes are also described, including techniques to condition the membrane. A formation of a particularly preferred membrane electrode assembly is also defined.

The present invention also defines flow field designs which facilitate supplying the liquid fuel to the catalyst.

5 The fuel cell system eventually needs to be used in a final product. This final product could be an internal combustion engine or could be much simpler electronic devices, such as a radio. Any electrically-driven product could operate based on electrical power produced from these fuel cells. The inventors of the present invention have
10 discovered certain techniques to improve the operation and ameliorate these problems which might otherwise exist.

The techniques of the present invention also enable a "system operation" by describing techniques to operate the fuel cell as part of an overall system.

15 These system techniques includes sensors for measuring methanol concentration and other important parameters. The inventors realized that various sensors for various parameters would be necessary. The inventors could not find a commercial sensor. The present invention
20 describes a way of modifying the techniques which they use in their fuel cell to form a sensor. This sensor operates

with high reliability using the techniques of this fuel cell.

Another technique defines formation of monopolar cells.

5 Brief Description of the Drawings

These and other aspects of the invention will now be described in detail with reference to the accompanying drawings, wherein:

Figures 1 and 2 show a basic fuel cell according to
10 the present invention;

Figure 3 shows the drying dish used for drying teflon encoded carbon paper sheets;

Figure 4 shows the basic platinum sputtering device of the present invention;

15 Figure 5 shows a basic flow field apparatus according to the first embodiment of the present invention;

Figure 6 shows a cross-sectional view of the preferred flow field along the line 66 in Figure 5;

Figure 7 shows a first embodiment of the structure
20 of the biplate of the present invention;

Figure 8 shows a second embodiment of the biplate structure;

Figure 9 shows a system operation of the direct methanol field fuel cell;

5 Figure 10 shows how the fuel cell concepts described above would be modified for use in a methanol sensor;

Figure 11 shows the methanol concentration versus current relationship of the present invention;

10 Figure 12 shows a graded molecular sieve fuel cell for methanol according to the present invention;

Figure 13 shows a first, expanded, figure of a monopolar approach to a fuel cell of the present invention;

Figure 14 shows the packaging of this monopolar approach;

15 Figure 15 shows a second embodiment of the monopolar approach in expanded view;

Figure 16 shows how this monopolar approach would be assembled into an operating system; and

20 Figure 17 shows the different expanded layouts of the monopolar approach assembly.

Description of the Preferred Embodiment

The liquid feed system described in our above noted patent uses a platinum-ruthenium catalyst on the anode and a platinum catalyst on the cathode. A perfluorsulfonic acid membrane, preferably DuPont's Nafion 117, is used as the
5 polymer electrolyte membrane.

Importantly, this system operated without the necessity for any acid electrolyte, or reformer. Various characteristics of various materials were changed to allow this improvement.

10 The anode electrode was made more hydrophilic using an ionomeric additive to improve access of the methanol water solutions to the anode surface.

An alternative way of making the anode more hydrophilic was to use an electrolyte which included a super
15 acid ("a C8 acid").

Alternative methanol derivative fuels, such as trimethoxymethane "TMM", reduce fuel crossover due to their increased molecule size, and other characteristics.

Fig. 1 illustrates a liquid feed organic fuel cell
20 10 having a housing 12, an anode 14, a cathode 16 and a solid polymer proton-conducting cation-exchange electrolyte membrane 18. As will be described in more detail below,

anode 14, cathode 16 and solid polymer electrolyte membrane 18 are preferably a single multi-layer composite structure, referred to herein as a membrane-electrode assembly. A pump 20 is provided for pumping an organic fuel and water solution into an anode chamber 22 of housing 12. The organic fuel and water mixture is withdrawn through an outlet port 23 and is re-circulated through a re-circulation system described below with reference to Fig. 2 which includes a methanol tank 19. Carbon dioxide formed in the anode compartment is vented through a port 24 within tank 19. An oxygen or air compressor 26 is provided to feed oxygen or air into a cathode chamber 28 within housing 12. Fig. 2, described below, illustrates a fuel cell system incorporating a stack of individual fuel cells including the re-circulation system. The following detailed description of the fuel cell of Fig. 1 primarily focuses on the structure and function of anode 14, cathode 16 and membrane 18.

Prior to use, anode chamber 22 is filled with the organic fuel and water mixture and cathode chamber 28 is filled with air or oxygen. During operation, the organic fuel is circulated past anode 14 while oxygen or air is pumped into chamber 28 and circulated past cathode 16. When

an electrical load (not shown) is connected between anode 14 and cathode 16, electro-oxidation of the organic fuel occurs at anode 14 and electro-reduction of oxygen occurs at cathode 16. The occurrence of different reactions at the anode and cathode gives rise to a voltage difference between the two electrodes. Electrons generated by electro-oxidation at anode 14 are conducted through the external load (not shown) and are ultimately captured at cathode 16. Hydrogen ions or protons generated at anode 14 are transported directly across membrane electrolyte 18 to cathode 16. Thus, a flow of current is sustained by a flow of ions through the cell and electrons through the external load.

As noted above, anode 14, cathode 16 and membrane 18 form a single composite layered structure. In a preferred implementation, membrane 18 is formed from Nafion™, a perfluorinated proton-exchange membrane material. Nafion™ is a co-polymer of tetrafluoroethylene and perfluorovinylether sulfonic acid. Other membrane materials can also be used. For example, membranes of modified perfluorinated sulfonic acid polymer, polyhydrocarbon sulfonic acid and composites of two or more kinds of proton exchange membranes can be used.

Anode 14 is formed from platinum-ruthenium alloy particles either as fine metal powders, i.e. "unsupported", or dispersed on high surface area carbon, i.e. "supported". The high surface area carbon may be material such as Vulcan XC-72A, provided by Cabot Inc., USA. A carbon fiber sheet backing (not shown) is used to make electrical contact with the particles of the electrocatalyst. Commercially available Toray™ paper is used as the electrode backing sheet. A supported alloy electrocatalyst on a Toray™ paper backing is available from E-Tek, Inc., of Framingham, Massachusetts. Alternately, both unsupported and supported electrocatalysts may be prepared by chemical methods, combined with Teflon™ binder and spread on Toray™ paper backing to produce the anode. An efficient and time-saving preferred method of fabrication of electro-catalytic electrodes is described in detail hereinbelow.


Platinum-based alloys in which a second metal is either tin, iridium, osmium, or rhenium can be used instead of platinum-ruthenium. In general, the choice of the alloy depends on the fuel to be used in the fuel cell. Platinum-ruthenium is preferable for electro-oxidation of methanol. For platinum-ruthenium, the loading of the alloy particles

in the electrocatalyst layer is preferably in the range of 0.5 - 4.0 mg/cm². More efficient electro-oxidation is realized at higher loading levels, rather than lower loading levels.

5 Cathode 16 is a gas diffusion electrode in which platinum particles are bonded to one side of membrane 18. Cathode 16 is preferably formed from unsupported or supported platinum bonded to a side of membrane 18 opposite to anode 14. Unsupported platinum black (fuel cell grade)
10 available from Johnson Matthey Inc., USA or supported platinum materials available from E-Tek Inc., USA are suitable for the cathode. As with the anode, the cathode metal particles are preferably mounted on a carbon backing material. The loading of the electrocatalyst particles onto the carbon
15 backing is preferably in the range of 0.5-4.0 mg/cm². The electrocatalyst alloy and the carbon fiber backing contain 10-50 weight percent Teflon™ to provide hydrophobicity needed to create a three-phase boundary and to achieve efficient removal of water produced by electro-reduction of
20 oxygen.


During operation, a fuel and water mixture (containing no acidic or alkaline electrolyte) in the concentra-

tion range of 0.5 - 3.0 mole/liter is circulated past anode 14 within anode chamber 22. Preferably, flow rates in the range of 10 - 500 ml/min. are used. As the fuel and water mixture circulates past anode 14, the following electro-chemical reaction, for an exemplary methanol cell, occurs releasing electrons:



Carbon dioxide produced by the above reaction is withdrawn along with the fuel and water solution through outlet 23 and separated from the solution in a gas-liquid separator (described below with reference to Fig. 2). The fuel and water solution is then re-circulated into the cell by pump 20.

Simultaneous with the electrochemical reaction described in equation 1 above, another electrochemical reaction involving the electro-reduction of oxygen, which captures electrons, occurs at cathode 16 and is given by:



The individual electrode reactions described by equations 1 and 2 result in an overall reaction for the exemplary methanol fuel cell given by:



At sufficiently high concentrations of fuel, current densities greater than 500 mA/cm can be sustained. However, at these concentrations, a crossover rate of fuel across membrane 18 to cathode 16 increases to the extent that the efficiency and electrical performance of the fuel cell are reduced significantly. Concentrations below 0.5 mole/liter restrict cell operation to current densities less than 100 mA/cm². Lower flow rates have been found to be applicable at lower current densities. High flow rates are required while operating at high current densities to increase the rate of mass transport of organic fuel to the anode as well as to remove the carbon dioxide produced by electrochemical reaction. Low flow rates also reduce the crossover of the fuel from the anode to the cathode through the membrane.

Preferably, oxygen or air is circulated past cathode 16 at pressures in the range of 10 to 30 psig. Pressures

greater than ambient improve the mass transport of oxygen to the sites of electrochemical reactions, especially at high current densities. Water produced by electrochemical reaction at the cathode is transported out of cathode chamber 28
5 by flow of oxygen through port 30.

In addition to undergoing electro-oxidation at the anode, the liquid fuel which is dissolved in water permeates through solid polymer electrolyte membrane 18 and combines with oxygen on the surface of the cathode electrocatalyst.
10 This process is described by equation 3 for the example of methanol. This phenomenon is termed "fuel crossover". Fuel crossover lowers the operating potential of the oxygen electrode and results in consumption of fuel without producing useful electrical energy. In general, fuel crossover is a
15 parasitic reaction which lowers efficiency, reduces performance and generates heat in the fuel cell. It is therefore desirable to minimize the rate of fuel crossover. The rate of crossover is proportional to the permeability of the fuel through the solid electrolyte membrane and increases with
20 increasing concentration and temperature. By choosing a solid electrolyte membrane with low water content, the permeability of the membrane to the liquid fuel can be reduced.

Reduced permeability for the fuel results in a lower crossover rate. Also, fuels having a large molecular size have a smaller diffusion coefficient than fuels which have small molecular size. Hence, permeability can be reduced by choosing a fuel having a large molecular size. While water soluble fuels are desirable, fuels with moderate solubility exhibit lowered permeability. Fuels with high boiling points do not vaporize and their transport through the membrane is in the liquid phase. Since the permeability for vapors is higher than liquids, fuels with high boiling points generally have a low crossover rate. The concentration of the liquid fuel can also be lowered to reduce the crossover rate. With an optimum distribution of hydrophobic and hydrophilic sites, the anode structure is adequately wetted by the liquid fuel to sustain electrochemical reaction and excessive amounts of fuel are prevented from having access to the membrane electrolyte. Thus, an appropriate choice of anode structures can result in the high performance and desired low crossover rates.

Because of the solid electrolyte membrane is permeable to water at temperatures greater than 60°C, considerable quantities of water are transported across the membrane

by permeation and evaporation. The water transported through the membrane is condensed in a water recovery system and fed into a water tank (both described below with reference to Fig. 2) so that the water can be re-introduced into anode chamber 22.

Protons generated at anode 14 and water produced at cathode 16 are transported between the two electrodes by proton-conducting solid electrolyte membrane 18. The maintenance of high proton conductivity of membrane 18 is important to the effective operation of an organic/air fuel cell. The water content of the membrane is maintained by providing contact directly with the liquid fuel and water mixture. The thickness of the proton-conducting solid polymer electrolyte membranes should preferably be in the range from 0.05 - 0.5 mm. Membranes thinner than 0.05 mm may result in membrane electrode assemblies which are poor in mechanical strength, while membranes thicker than 0.5 mm may suffer extreme and damaging dimensional changes induced by swelling of the polymer by the liquid fuel and water solutions and also exhibit excessive resistance. The ionic conductivity of the membranes should be greater than 1 ohm⁻¹


cm² for the fuel cell to have a tolerable internal resistance.

As noted above, the membrane should have a low permeability to the liquid fuel. Although a Nafion™ membrane has been found to be effective as a proton--conducting solid polymer electrolyte membrane, perfluorinated sulfonic acid polymer membranes such as Aciplex™ (manufactured by Asahi Glass Co., Japan) and polymer membranes made by Dow Chemical Co., Japan) and polymer membranes made by Dow Chemical Co., USA, such as XUS13204.10 which are similar to properties to Nafion™ are also applicable. Membranes of polyethylene and polypropylene sulfonic acid, polystyrene sulfonic acid and other polyhydrocarbon-based sulfonic acids (such as membranes made by RAI Corporation, USA) can also be used depending on the temperature and duration of fuel cell operation. Composite membranes consisting of two or more types of proton-conducting cation-exchange polymers with differing acid equivalent weights, or varied chemical composition (such as modified acid group or polymer backbone), or varying water contents, or differing types and extent of cross-linking (such as cross linked by multivalent cations e.g., Al 3+, Mg

2+ etc.,) can be used to achieve low fuel permeability. Such composite membranes can be fabricated to achieve high ionic conductivity, low permeability for the liquid fuel and good electrochemical stability.

5 As can be appreciated from the foregoing description, a liquid feed direct oxidation organic fuel cell is achieved using a proton-conducting solid polymer membrane as electrolyte without the need for a free soluble acid or base electrolyte. The only electrolyte is the
10 proton-conducting solid polymer membrane. No acid is present in free form in the liquid fuel and water mixture. Since no free acid is present, acid-induced corrosion of cell components, which can occur in current-art acid based organic/air fuel cells, is avoided. This offers
15 considerable flexibility in the choice of materials for the fuel cell and the associated sub-systems. Furthermore, unlike fuel cells which contain potassium hydroxide as liquid electrolyte, cell performance does not degrade because soluble carbonates are not formed. A solid
20 electrolyte membrane also minimizes parasitic shunt currents.

Further Improvements. The reactions of the direct methanol/liquid-fed fuel cell are as follows:



The present specification describes various improvements in manufacturing and forming the preferred structure and materials used according the present invention.

Various experiments carried out by the inventors have ascertained that one particular preferred catalyst material is platinum-ruthenium ("Pt-Ru"). Various formulations allowing combination of those two metals are possible. The inventors found that a bimetallic powder, having separate platinum particles and separate ruthenium particles produced a better result than a platinum-ruthenium alloy. The preferred Pt-Ru material used according to the present invention has a high surface area to facilitate contact between the material and the fuels. Both platinum and ruthenium are used in the catalytic reaction, and the inventors found that it was important that the platinum and

ruthenium compounds be uniformly mixed and randomly spaced throughout the material, i.e., the material must be homogeneous.

A first aspect of the present invention combines
5 different metals to form a platinum-ruthenium bimetallic powder which has distinct sites of different materials. While there is some combination between the particles, the techniques of the present invention ensure that the extent of combination is minimal.

10 The process of forming the preferred materials is described herein. First, a slurry of platinum salts and ruthenium salts in hydrochloric acid is formed.

A chloroplatinic acid hexahydrate salt $H_2PtCl_6 \cdot 6H_2O$ is formed by dissolving chloroplatinic acid
15 crystals in hydrochloric acid.

A ruthenium salt $K_2RuCl_5 \cdot H_2O$ is formed from potassium pentachloroaquoruthenium (III).

12.672 grams of chloroplatinic acid crystals are mixed with 13.921 grams of potassium
20 pentachloroaquoruthenium crystals and 600 ml of 1 molar hydrochloric acid. The mixture of acid and salt is stirred for 15 to 30 minutes to obtain a homogeneous mixture.

The acid slurry is then neutralized and precipitated by addition of 140 grams of sodium carbonate (Na_2CO_3) per ml per minute at between 20-30°C. During this time, carbon dioxide will vigorously evolve from the solution. The sodium carbonate is continuously added until the gas evolution ceases. At this time, the solution turns brown-black. The inventors found that this took about 15 minutes.

Maintaining proper pH during this operation is important -- the pH should be maintained at around 9.25 by the slow addition of sodium carbonate.

The "grey powdery mass" is then processed to evaporate water from the slurry. The evaporation takes between 1 and 2 hours and eventually forms a black gluey solid with dry lumps of the material. The black gluey solid is then dried in a vacuum or in flowing nitrogen at 80 to 100°C. A lumpy grey solid is obtained. This solid includes materials which are still in solution with the sodium chloride.

The chemical content of the grey powdery mass
Ruthenium hydroxide - $\text{Ru}(\text{OH})_3$, Platinum hydroxide - $\text{Pt}(\text{OH})_4$,
and "gunk" or chlorides, plus excess Na_2CO_3 .

The inventors postulate that these extra materials maintain the separation between the platinum and the ruthenium. If the materials were maintained alone, they would sinter, causing them to join and increase particle size. The carbonate buffer between the particles prevents coalescing.

This lumpy solid material is then reduced in a hydrogen and argon atmosphere to reduce the salt to a metal. The material is transferred into a glass boat. The boat is placed in the center of a glass tube of a tubular furnace. In a gaseous mixture of 7% hydrogen, 93% argon or alternatively in a mixture of hydrogen/nitrogen, the material is reduced at around 225°C. The gas should be flowing over the boat at a rate of 50 to 200 ml per minute.

The gas flow is maintained in the heated atmosphere for 14 hours. Then, with hydrogen still flowing over the powder, the catalyst powder is allowed to cool to around 40°C. This forms a mixture of particles of platinum, ruthenium, plus other chlorides and carbonates.

The resulting material must then be washed. The material takes several washes, e.g. six washes at 60°C.

Each wash transfers the sample in the glass boat to a beaker having 1 liter of de-ionized water at 60°C.

Platinum-ruthenium is water insoluble. Hence, the washings do not effect the platinum ruthenium materials, and only removes the other materials. Each washing includes stirring the water solution for 15 minutes, to dissolve the soluble chlorides and carbonates. Since the metal particles are of submicron size, they do not settle to the bottom, but instead form a colloidal mixture.

The solution is allowed to cool to 40°C. The solution is later centrifuged at 3000 rpm for one hour. The centrifuging process leaves a clear supernatant liquid. The supernatant liquid is transferred off, and the black sediment is transferred to a flask having 1 liter of 60° de-ionized water. This further washing removes any dissolved chlorides.

This washing process is repeated a total of six times. It has been found that stirring the water and centrifuging is important for total removal of the chlorides. These chlorides are harmful to catalyst performance. However, the inventors found that these

chlorides are a necessary binder to minimize the material coalescing but should be removed later.

After the final centrifuging operation, the powder is transferred to a beaker and dried in a vacuum oven at
5 60°C for three hours. Alternatively, the material can be freeze-dried. This results in a free-flowing submicron size active platinum-ruthenium catalyst. It is important to note that the dried materials have submicron sizes and hence they can easily become airborne. A submicron mask must be worn
10 to ensure safety.

The active catalyst powder has been found to include a homogeneous mixture of submicron size platinum particles and ruthenium particles. There are also some trace residuals of RuO_2 , ruthenium oxide, and ruthenium alloy.

15 This powder is used as a catalyst on the anode as described herein.

The platinum salt and ruthenium salt which are the initial products of this conversion can also be modified by adding titanium dioxide (TiO_2), iridium (Ir) and/or osmium
20 (Os). These materials can be used to improve the fuel cell performance at relatively nominal cost.

A comparison with the prior art particles shows the significant advantages of this process. The prior art particles form 5 micron size particles. These particles included ruthenium dioxide. An analysis of the particles of the present invention shows a homogeneous mixture down to the point of micron particle size. Under a scanning electron microscope there are no bright and dull spots- all materials appear to be totally grey. This shows that the mixing process has formed a totally homogeneous material.

The material prepared according to this process is called anode catalyst material. Further processing of this anode catalyst by combining with nafion solution, etc. results in an "ink". As described herein, this includes a combination of platinum metal and ruthenium metal. The inventors have found the preferred ratio of platinum to ruthenium can be between 60/40 and 40/60. The best performance is believed to occur at 60% platinum, 40% ruthenium. Performance degrades slightly as the catalyst becomes 100% platinum. It degrades more sharply as the catalyst becomes 100% ruthenium.

Other additions are added to the salt to improve characteristics and to replace the catalyst materials by

other less-expensive materials. The inventors realized that this fuel cell must be formed from inexpensive material. Unfortunately, platinum is an extremely expensive material. As of today's writing, platinum-ruthenium is the best
5 material for the catalyst. The inventors have investigated using replacements for all or part of the platinum in the catalyst. The substitution is based on the way that the platinum-ruthenium catalyst works.

The reaction which occurs at the anode is $\text{CH}_3\text{OH} + \text{H}_2\text{O}$
10 $\rightarrow \text{CO}_2 + \text{H}^+ + \text{e}^-$. The inventors believe that platinum-ruthenium catalyzes this reaction by aiding in disassociating the materials on the catalyst surface. The material draws the electrons out, and allows them to disassociate. The reaction can be explained as follows.

15 Methanol is a carbon compound. The carbon atom is bound to four other atoms. Three of the bonds are to hydrogen atoms. The other bond is to a hydroxyl, OH, group. The platinum disassociates methanol from its hydrogen bonds, to form:

20 $\text{M}=\text{C}-\text{OH}$ (M is the Pt or other metal site catalyst) + 3H^+ .
The ruthenium disassociates the hydrogen from the water molecule (HOH) to form M-OH. These surface species then

reassemble as $\text{CO}_2 + 6\text{H}^+ + 6\text{e}^-$. The H^+ (protons) are produced at the anode, and cross the anode to the cathode where they are reduced. This is called a bifunctional catalyst.

Any material which has a similar function of
5 disassociating the methanol and water as described can be used in place of the platinum. The inventors have investigated several such materials. They found alternatives to platinum including palladium, tungsten, Rhodium, Iron, Cobalt, and Nickel which are capable of
10 dissociating C-H bonds. Molybdenum (MoO_3), niobium (Nb_2O_5), zirconium (ZrO_2), and rhodium (Rh) may also be capable of dissociating H - OH as M - OH. A combination of these are therefore good catalysts. The catalyst for dissociating the H-O-H bonds preferably includes Ru, Ti, Os, Ir, Cr, and/or
15 Mn.

Ruthenium can be replaced either wholly or partly by a ruthenium-like material. The inventors found that iridium has many characteristics which are similar to ruthenium. A first embodiment of this aspect, therefore, uses a
20 combination of platinum, ruthenium and iridium in the relative relationship 50-25-25. This adds the salt H_2IrCl_6 .

H₂O to the initial materials described above, in appropriate amounts to make a 50-25-25 (Pt-Ru-Ir) combination.

It has been found that this catalyst also operates quite well, using less ruthenium.

5 Another material which has been found to have some advantages is material including titanium compounds. Any titanium alkoxide or titanium butoxide, e.g. titanium isopropoxide or TiCl₄, - can also be added to the original mixture. This forms an eventual combination of platinum-
10 ruthenium - TiO₂, also formed in a 50-25-25 (Pt-Ru-TiO₂) combination.

Platinum-ruthenium-osmium is also used. Osmium is added to the mixture as a salt H₂OsCl₆ · 6H₂O, and has also been found to produce advantageous properties.

15 However formed, these materials used to form the platinum ink must be applied to the anode. Various techniques can be used to apply this material. Formation of the anode, therefore, is described next.

Carbon paper formation.

20 Fuel crossover is a source of inefficiency in this fuel cell. Fuel crossover in this fuel cell occurs when

methanol passes through the anode instead of reacting at the anode. The methanol passes through the anode, the membrane electrode assembly, through the membrane and then through the cathode. The methanol may react at the cathode: this
5 lowers the efficiency of the fuel.

The electrodes of the present invention are preferably formed using a base of carbon paper. The starting material point is TGPH-090 carbon paper available from Toray, 500 Third Avenue, New York, New York. This
10 paper, however, is first pre-processed to improve its characteristics. The pre-processing uses a DuPont "Teflon 30" suspension of about 60% solids.

The paper can alternately be chopped carbon fibers mixed with a binder. The fibers are rolled and then the
15 binder is burned off to form a final material which is approximately 75% porous. Alternately, a carbon cloth paper could be used. This will be processed according to the techniques described herein. Alternately, a carbon paper cloth could be used. This will be processed according to
20 the techniques described herein to form a gas diffusion/ current collector backing.

The preferably processed carbon paper includes paper within embedded teflon particles. The spaces between the teflon particles should preferably be small enough to prevent methanol from passing therethrough. Even better characteristics are used when other methanol derivatives, such as TMM are used. The anode assembly is formed on a carbon paper base. This carbon paper is teflonized, meaning that teflon is added to improve its properties. The inventors have found that there is an important tradeoff between the amount of teflon which is added to the paper and its final characteristics.

It is important to maintain a proper balance of the amount of teflon used, as described herein.

The paper is teflonized to make it water repellent, and to keep the platinum ink mix from seeping through the paper. The paper needs to be wettable, but not porous. This delicate balance is followed by dipping and heating the paper. The inventors found a tradeoff between the degree of wettability of the paper and the amount of impregnation into the paper, which is described herein.

First, the Teflon 30 emulsion must be diluted. One gram of Teflon 30 is added to each 17.1 grams of water. One

gram of Teflon 30 of weight 60% corresponds to 60 grams of teflon per 100 ml. This material is poured into a suitable container such as a glass dish. The carbon paper is held in the material until soaked.

5 The soaking operation corresponds to weighing a piece of carbon paper, then dipping it into the solution for about 10 seconds or until obviously wet. The carbon paper is removed from the solution with tweezers, making as little contact with the paper as possible. However, the
10 characteristics of teflon are such that the tweezers themselves will attract the teflon, and cause an uneven distribution of fluid. Teflon-coated tweezers are used to minimize this possibility. The carbon paper is held with a corner pointing down, to allow excess solution to drain off.

15 Teflon emulsion's surface tension characteristics are such that if the material were laid on a glass surface, a lot of the teflon would be dragged out by surface tension. Instead, a paper-drying assembly is formed as shown in Figure 3. A plurality of teflon-covered wires 202 are
20 stretched over a catchbasin such as a dish 200. The stretched wires form two sets of orthogonally-extending

supports 202 and 204. The carbon paper which has just been treated with teflon solution is held across these supports.

Ideally, the wires are teflon-coated wires having a diameter of 0.43 inches. While these dimensions are not
5 critical, a smaller amount of contact with the paper makes the suspension distribution on the wire more even. Kinks 206 are formed in the wires to prevent the carbon paper from touching the wires all along its length and hence further minimize the area of contact.

10 The paper-drying assembly shown in Fig. 3 is then placed into an oven at 70°C for one hour. The treated carbon papers are removed from the dish after drying, and placed into glass containers. These are then sintered in a furnace oven at 360°C for one hour. A properly processed
15 paper will have its weight increased by 5% over the course of this process. More generally, any weight increase between 3 and 20% is acceptable. The paper is weighed to determine if enough absorption has occurred and/or if further paper processing will be necessary.

20 This substrate plus a catalyst layer forms the eventual electrode.

Two preferred techniques of application of the catalyst including layer are described herein: a direct application and a sputtering application. Both can use the special carbon paper material whose formation was described
5 above, or other carbon paper including carbon paper which is used without any special processing. The direct application technique of the present invention mixes materials with the platinum-ruthenium material described above or any other formulation, more generally, catalyst materials. The
10 catalyst materials are processed with additional materials which improve the characteristics.

Platinum-ruthenium powder is mixed with an ionomer and with a water repelling material. The preferred materials include a solution of perfluorsulfonic acid
15 (Nafion) and teflon micro-particles. 5 grams of platinum-ruthenium powder are added per 100 ml of Nafion in solvent.

A DuPont T-30 mix of 60% teflon solid by weight appropriately diluted is added. These teflon micro-particles are then mixed. Preferably, a dilute Teflon 30
20 suspension of 12 weight percent solids including 1 gram of Teflon 30 concentrate to 4 grams of de-ionized water is made. 300 mg of de-ionized water is added to 350 mg of the

12 weight % teflon solution described above. 144 mg of platinum-ruthenium is mixed to this solution. The resultant mixture is then mixed using an ultrasonic mixing technique known in the art as "sonicate". The ultrasonic mixing is preferably done in an ultrasonic bath filled with water to a depth of about 1/4 inch. The mixture is "ultrasonicated" for about 4 minutes.

It is important that the Teflon must first be mixed with the platinum-ruthenium as described above to form about 15% by weight teflon. Only after this mixture is made can the Nafion be added. The inventors have found that if Nafion is added first, it may surround the particles of platinum and ruthenium. Therefore, the order of this operation is critically important. At this point, 0.72 grams of 5 weight % Nafion is added to the jar, which is sonicated again for 4 minutes. More generally, approximately 1 mg of Nafion needs to be added per square cm of electrode to be covered. The amount of teflon described above may also be modified, e.g. by adding only 652 ml of the solution.

This process forms a slurry of black material. This slurry of black material is then applied to the carbon

paper. The application can take any one of a number of forms. The simplest form is to paint the material on the carbon paper backing, using alternating strokes in different directions. A small camel hair brush is used to paint this
5 on. The preferred material amounts described above, to form enough catalyst for one side of a 2-inch by 2-inch piece of 5 weight % teflonized carbon paper. Accordingly, the painting is continued until all the catalyst is used.

A drying time of two to five minutes between coats
10 should be allowed, so that the material is semi-dried between coats and each coat should be applied in a different direction. The anode needs to then dry for about 30 minutes. After that 30 minutes, the anode must be "pressed" immediately. The pressing operation is described herein.

15 The resulting structure is a porous carbon substrate used for diffusing gases and liquids, covered by 4 per square cm of catalyst material.

An alternative technique of applying the materials sputters the materials onto the backing.

20 We have now described how to form the anode. Next, the techniques involved in forming the preferred proton

conducting membrane (the Nafion) and then the techniques in forming the cathode will be described.

Proton Conducting Membrane - The preferred material described herein is Nafion 117. However, other materials
5 can also be used to form proton conducting membranes. For example, other perfluorsulfonic acid materials can be used. It is postulated that different materials with carboxylic acid groups can also be used for this purpose.

The preferred embodiment starts with Nafion 117,
10 available from DuPont. This material is first cut to the proper size. Proper sizing is important, since the end materials will be conditioned. First, the Nafion is boiled in a hydrogen peroxide solution. A 5% solution of hydrogen peroxide is obtained, and the membrane is boiled in this
15 solution for 1 hour in 80-90°C. This removes any oxidizable organic impurities.

Following this peroxide boiling step, the membrane is boiled in de-ionized water, at close to 100°C, for 30 minutes. Hydrogen peroxide which was previously adsorbed
20 into the membrane is removed along with other water-soluble organic materials.

The thus-processed membrane is next boiled in a sulfuric acid solution. A one molar solution of sulfuric acid is prepared by diluting commercially available 18-molar concentrated ACS-grade sulfuric acid. The ACS-grade acid
5 should have metal impurities in an amount less than 50 parts per million. The membrane is boiled in the 1-molar sulfuric acid at about 100°C to more completely convert the material into a proton conducting form.

The processed material is next boiled in de-ionized
10 water at 90-100°C for thirty minutes. The water is discarded, and this boiling step is repeated three more times to purify the membrane.

After these washings, the membrane is free of sulfuric acid and in completely "protonic" form. The
15 membrane is stored in de-ionized water in a sealed container until it is ready for further processing.

Cathode construction. The cathode is constructed by first preparing a cathode catalyst ink. The cathode catalyst ink is preferably pure platinum, although other
20 inks can be used and other materials can be mixed into the ink as described herein. 250 mg of platinum catalyst is mixed with 0.5 gram of water including 37-1/2 mg of teflon.

The mix is sonicated for five minutes and combined with a 5% solution of Nafion. The mix is again sonicated for five minutes to obtain a uniform dispersal. This forms enough material to cover one piece of 2x2" carbon paper.

- 5 Unprocessed Toray carbon paper can be used with no teflon therein. However, preferably the material is teflonized as discussed above. The procedures are followed to make a 5% teflon impregnated paper. The paper is then heated at 300°C for one hour to sinter the teflon particles. Catalyst ink
10 is then applied to the paper as described above to cover the material with 4 mg/cm²/g of PT. Teflon content of the paper can vary from 3-20%, 5% being the preferred.

Sputtering

- An alternative technique of cathode forming forms a
15 sputtered platinum electrode. This sputtered platinum electrode has been found to have significant advantages when used as a plain air electrode. The process of forming the sputtered platinum electrode is described herein.

- The cathode electrode carries out a reaction of $O_2 +$
20 $H^+ + e^- \rightarrow$ water. The O_2 is received from the ambient gas around the platinum electrode, while the electron and protons are received through the membrane. This alternative

technique for forming the cathode electrode starts with fuel cell grade platinum. This can be bought from many sources including Johnson-Matthey. 20 to 30 gms per square meter of surface area of this platinum are applied to the electrode
5 at a particle size of 0.1 to 1 micron.

A platinum source is a solid rod of material. According to this embodiment, the material is sputtered onto the substrate prepared as described above. The platinum powder is first mixed with aluminum powder. This mixing can
10 be carried out using mechanical means for example, or it can be done using salt combination techniques as described above for the formulation of the anode ink. The platinum-aluminum mixture is sputtered onto the carbon paper backing using any known sputtering technique from the semiconductor arts.

15 The platinum is sputtered as follows using the system diagrammed in Figure 4. A standard 4-inch target 250 holds the carbon paper electrode 252. The target is rotated by a motor 254 at one rotation between per 10 seconds. The preferred technique used herein sputters platinum from a
20 first Pt source and aluminum from an Al source 262. The platinum is sputtered to 0.23 amps and the aluminum at 0.15 amps at around 200 volts. The two sources impinge from

different directions in opposite sides towards the targets at 45° angles.

The inventors found that 20 Torr was the ideal pressure for this sputtering, although any pressure between 1 to and 50 to could be used. The Argon pressure is about 30 mtorr. However, different argon pressures can be used to form different particle sizes. The sputtering is done for about 8 minutes.

Preferably, once sputtered, the etching is carried out by dipping the sputtered backing into an etching solution, followed by a washing solution followed by dipping.

The sputtered electrode is a mixture of Al and Pt particles on the backing. The electrode is washed with potassium hydroxide (KOH) to remove the aluminum particles. This forms a carbon paper backing with very porous platinum thereon. Each of the areas where the aluminum was formed is removed -- leaving a pore space at that location. The inventors found that a thick coating of the Pt-Al material would prevent washing out the Al from some lower areas of the catalyst. The present invention uses a thin coating -

preferably a 0.1 micron coating or less with a material density between 0.2 mg per cm² and 0.5 mg per cm².

At this point in the processing, we now have an anode, a membrane, and a cathode. These materials are
5 assembled into a membrane electrode assembly ("MEA")

MEA Formation

The electrode and the membranes are first laid or stacked on a CP-grade 5 Mil, 12-inch by 12-inch titanium foil. Titanium foil is used by the present inventors to
10 present any acid content from the membrane from leaching into the foil.

First, the anode electrode is laid on the foil. The proton conducting membrane has been stored wet to maintain its desired membrane properties. The proton
15 conducting membrane is first mopped dry to remove the macro-sized particles. The membrane is then laid directly on the anode. The cathode laid on top of the membrane. Another titanium foil is placed over the cathode.

The edges of the two titanium foils are clipped
20 together to hold the layers of materials in position. The titanium foil and the membrane between which the assembly is

to be pressed includes two stainless steel plates which are each approximately 0.25 inches thick.

The membrane and the electrode in the clipped titanium foil assembly is carefully placed between the two stainless steel platens. The two platens are held between jaws of a press such as an arbor press or the like. The press should be maintained cold, e.g. at room temperature.

The press then actuated to develop a pressure between 1000 and 1500 psi, with 1250 psi being an optimal pressure. The pressure is held for 10 minutes. After this 10 minutes of pressure, heating is commenced. The heat is slowly ramped up to about 146°C; although anywhere in the range of 140-150°C has been found to be effective. The slow ramping up should take place over 25-30 minutes, with the last 5 minutes of heating being a time of temperature stabilization. The temperature is allowed to stay at 146°C for approximately 1 minute. At that time, the heat is switched off, but the pressure is maintained.

The press is then rapidly cooled using circulating water, while the pressure is maintained at 1250 psi. When the temperature reaches 45°C, approximately 15 minutes

later, the pressure is released. The bonded membrane and electrodes are then removed and stored in de-ionized water.

Flow Field. A fuel cell works properly only if fuel has been properly delivered to the membrane to be reacted
5 an/or catalyzed. The membrane electrode assembly of the present invention uses a flow field assembly as shown in Fig. 5. Each membrane electrode assembly ("MEA") 302 is sandwiched between a pair of flow-modifying plates 304 and 312 which include biplates and end plates. A flow of fuel
10 is established in each space 303 between each biplate/endplate and MEA. The collection of biplates/endplates and MEA forms a "stack". The biplate includes provisions for fluid flow at both of its oppositely-facing surfaces. The end flowplate of the stack
15 is an end plate 312 instead of a biplate. The endplate has chambers on one side only. The biplate 304 includes a plurality of separators 306 and a plurality of chamber forming areas 308. The separators 306 have the function of pressing against the membrane electrode assembly 302. The
20 end surface of separators 306 are substantially flat surfaces that contact the surface of the MEA 302.

The biplates are formed of an electrically conductive material in order to couple all the membrane electrode assemblies 302, 310 in series with one another.

Membrane electrode assemblies 302, as described
5 above include an anode, a membrane, and a cathode. The anode side 312 of each membrane electrode assembly is in contact with an aqueous methanol source in space 314. The cathode side of each membrane electrode assembly is in contact with an oxidant air source 316 which provides the
10 gaseous material for the reactions discussed above. The air can be plain air or can be oxygen.

Flows of these raw materials are necessary to maintain proper supply of fuel to the electrode. It is also desirable to maintain the evenness of the flow.

15 One stack design of the present invention uses the system shown in Figure 6. The fuel is supplied from fuel supply chamber 602, which is typically a high volume element which includes fuel under pressure. Narrow nozzle-like elements 604 cause a large pressure drop therealong. The
20 pressure drop in the thin line is much greater than any pressure drop along the supply. This evens the flow within the cells and among the cells.

A careful trade-off must be balanced between the amount of surface acting as a pressing element and the amount of surface that acts as a holding element.

It is desirable to apply even pressure against the
5 membrane electrode assembly 202 from both sides for many reasons. However, in places where the pressing surface 306 presses against the membrane, the membrane electrode assembly 302 cannot be directly in contact with the methanol. Instead it is pressed by the surface 315.
10 Therefore, that part of the surface of MEA 302 does not react. The different designs according to the present invention carry out various functions to improve the flow or improve some characteristic of its reliability.

Each of the nozzles 606 has a narrow width. The
15 outlet 605 of each nozzle 606 faces one island pressing area 608 which corresponds to a pressing surface 306. The supply of fuel from nozzle 606 is supplied directly against the interface surface 610 of island 608. The islands in Figure 6 are rectangular in shape. Interface surface 610 is a
20 narrow side of the rectangular island. The wider side of the island is parallel to the flow. All input flows face directly against one of the surfaces of an island.

The inventor found that this preferred narrow layout creates turbulence in the area of the islands 608. The turbulence stirs the fuel in the chamber and forms a more even flow through the system. This turbulence also
5 facilitates flow between each of the islands. The output flow is eventually received by output nozzles 612 and routed into output conduit 614. The output nozzles are analogously placed adjacent surfaces 620 of the islands, thus causing further turbulence.

10 The islands according to this embodiment are 50 mil on the interface side 610, and 150 mil on the wider side. The pressure drop across the stack is approximately 0.06 psi for the stack.

Other biplate configurations can also be used.

15 It is important that the biplates themselves be lightweight and thin, to allow increase of the stacking pitch as much as possible.

Graphite is difficult to machine, and is relatively thick. Graphite's advantages include its imperviousness to
20 liquid and gas.

A number of alternative solutions are used according to the present invention. A first modification of the present invention uses the system shown in Fig. 7.

Interface layer 702 forms a dense, conductive liquid
5 gas impervious layer. This reduces the amount of fuel, gas or liquid which can cross the biplate assembly over the materials. However, a dense porous material is used as the crossing areas 700. The porosity allows a certain amount of the material to seep into the MEA through this interface
10 layer.

The dense porous material can be conductive carbon, for example, which is much easier to machine than graphite. The seepage is stopped by interface material, which prevents the liquid and gas from crossing across the whole biplate.

15 The porosity of the pressing parts allows the liquid and gas to reach some of the parts of the membrane electrode assembly which are being pressed by the pressing element. The methanol hence may penetrate to these areas which would otherwise be less efficiently convecting.

20 The central binding layer 704 is low-density ("LD") carbon. LD carbon is relatively easy to work with and inexpensive. Since the LD carbon is covered at all

locations by graphite, however, its undesirable characteristics are mostly masked.

A second embodiment used to form a biplate is shown in Fig. 8. This second biplate embodiment uses a layered titanium-carbon ultrathin biplate. Any biplate should be thin; because we want the stack to be as thin as possible for any given voltage. Each membrane electrode assembly and biplate will produce a voltage when energized, we call that the inherent voltage. The inherent voltage, and the thickness of the device, sets the maximum possible volts-per-inch of thickness of the device of the present invention. One important component of the volts-per-thickness is the thickness of the biplate.

Figure 8 shows the second biplate embodiment of the present invention. This material uses a layered concept to form a biplate combining the best characteristics of the materials. A titanium carbide interface layer 800 is bonded to titanium bonding layer 802. The titanium bonding layer 802 is preferably 3 mils thick. These two layers together prevent migration of any protons across the biplates and also ensure adequate electrical bonding characteristics. The titanium materials are covered with separating materials

804 which include surfaces to hold the biplates in place. A certain measure of porosity is hence enabled as in the Figure 7 embodiment.

Of course, the titanium could be replaced by any
5 metal with similar conducting and chemically stable characteristics.

The inventors of the present invention recognize that the graphite material usually used must represent a trade-off between the competing necessities.

10 Efficiency of operation requires that fuel from one side of one biplate, e.g. the anode side, not seep across to the other side of the same biplate, which interfaces to a cathode. If the biplate were porous, the fuel materials could seep across. However, since no fluids can pass
15 through the biplates, this has meant that no fluids can reach the portions of the electron membrane assembly being pressed by the pressing surfaces biplates, e.g. 306. Therefore these portions of the membrane electrode assembly which are being pressed by those pressing surface are not
20 efficiently producing electrical activity. This lowers the overall efficiency of the cell.

These embodiment of the present invention provide a new kind of trade-off. The membrane electrode assembly is pressed by a porous portion of the biplate. This porous portion allows at least some of the fuel to reach that
5 portion of the electrode. This can improve the electrical operation of the MEA. This feature of the present invention also provides other bonded pieces which prevent the fluid from passing over into the other portions of the electrode membrane assembly.

10 System. The basic system of the present invention is shown in Fig. 9. The system is based on the inventor's recognition of ways of recycling the output of the fuel cell. The fuel cell consumes methanol or methanol derivatives, water and produces output products including
15 methanol or derivatives, water, and gases. Methanol represents the fuel that is to be consumed. Any fuel cell system would need to carry quantities of methanol fuel to be consumed. However, this reaction would also require equal amounts of water. The inventors recognized that the water
20 used in the reaction can be recycled from the cathode. This avoids the need to

The amount of power that a vehicle can produce is limited by its payload -- i.e. the weight of the vehicle and its occupants. All vehicles are limited in power by the amount of weight that they must carry. More weight limits a vehicle's power and hence makes the vehicle less efficient. For example, a passenger car usually does not hold more than 20-30 gallons of gasoline. This has been determined by many to represent an optimum trade-off between the distance that the vehicle can run before re-filling the tank, and the excess weight that would result from a larger fuel tank.

Vehicle engineers decide how much payload weight they are willing to allow. The inventors describe techniques which ensure that this weight is taken up by fuel, not water.

One of the features of the system of the present invention is to maintain the water balance so that most of the water is recycled and no substantial source of water needs to be carried.

The overall system is shown in Fig. 9. Methanol tank 900 stores pure methanol (or other methanol-type derivative fuel). A first liquid pump 902 pumps the methanol through a valve 904 to a circulation tank 906.

Water tank 908 provides a supply of water where necessary. The water is pumped by pump 910 through valve 912 to recirculation tank 906. A central controller 914 controls the overall operation of the entire system. Controller 914
5 controls the relative positions of the valves 904 and 912.

Methanol concentration sensor 916 is preferably located either in the methanol or very close to it. Methanol sensor 916 detects the concentration of methanol in the circulation tank, and controller 914 uses this
10 information to control further operation of the system.

The aqueous methanol in the circulation tank is maintained by this control system at 1-2 M. Therefore, the methanol in line 918 should also be of the proper concentration. Pump 920 pumps the methanol through a fuel
15 filter 922 to the membrane electrode stack 924. The stack used herein can be a similar stack to those described previously. The electrical output 926 of the stack 924 is sent to the motor to drive the payload and also drives controller 914 and other electrical systems such as the
20 compressor 930.

The stack is also driven with inlet air 932 through the compressor 930. Air filter 934 cleans the air prior to its introduction into the stack.

The fuel out of the stack includes two components:
5 water and methanol. Both components are processed using respective condensers 940 and 942 to lower the water temperature sufficiently to allow both the methanol and the water to condense. Fans 944 may be used to facilitate this cooling. The recycled methanol and water are both
10 resupplied to the circulation tank. The recycled methanol 946 from the output of the methanol stack, and the recycled air and water from the inlet air 952 recycle into circulation tank 906.

Fluid engineers have recognized that pumping gas is
15 extremely expensive in terms of energy resources, while pumping liquid is extremely inexpensive. One aspect of the present invention may require pressurizing the air to the cathode. For example, the air may need to be pressurized to 20 psi. However, the output air on line 944 (after reacting
20 with the cathode) will be almost as highly pressurized. This output air 944 will be pressurized to 19 psi. Accordingly, the output air 946 is coupled to a pressure-

driven turbine 946. This expander is run by pressure, and used to drive the air compressor 930. Without this recycling of the pressurized power, the air compressor might use as much as 20-30% of the power produced by the cell.

5 Expander output 948 includes an air and water combination. This water and air is separated to vent the exhaust air at 950, and the recycled water being returned to the circulation tank 902. A vent for excess water 954 may also be necessary. This vent is controlled by controller
10 914, and necessary at some time if too much water is being recirculated.



 As an alternative to the sensor and controller, the amount of fuel which is supplied can be metered. The fuel cell first starts its operation at room temperature.
15 However, the current fuel cell is intended to operate at about 90°C. The electrochemical fuel cell reaction will eventually heat up the fuel cell to the proper temperature.

 The present invention operates using methanol sensors. A particularly preferred methanol sensor uses MEA
20 technology described above. As described above, a fuel cell is formed of an anode and a cathode. The anode receives methanol. The cathode receives air or oxygen.

This sensor uses the modified fuel cell shown in Figure 10. A Pt-Ru anode 1002 is connected to a nafion electrolyte 1004, which is connected to a Pt cathode. The cathode is preferably larger than the anode, e.g., the
5 cathode is three times the area of the anode.

The cathode 1006 (and anode) are immersed in the methanol solution. Therefore, since the cathode 1006 is under fluid, it cannot react with air, and hence the H_2 cannot react to H_2O as in the basic fuel cell reaction.
10 Applying a voltage to the fuel cell changes, e.g. reverses, the reaction which occurs. Under current, the anode reacts directly with methanol to form CO_2 , and the cathode will change protons to hydrogen. A small cathode, and a large anode to reduce protons, further enhances the sensitivity of
15 this methanol electrode.

The reactions, therefore, include:



A constant voltage is applied by constant voltage
20 circuit 1010. Ammeter 1012 measures the current. Figure 11 shows the relationship between the current and the methanol concentration in the solution. Controller 1014, which can

be a process controller or microprocessor, looks up the closest methanol concentration corresponding to the measured current, using the plotted Fig 11 relationship.

Since the Figure 11 plot may be highly temperature
5 dependent, thermocouple 1016 may provide correction information.

Another important feature of the present invention is related to practical use of this system in an automotive environment. Practical use would require delivery of
10 methanol from the methanol equivalent of a gas pump. Methanol would have hydrocarbon impurities when taken from the gas pump. Such impurities would be very dangerous to the system described by the present invention which requires highly pure methanol. According to the present invention, a
15 fuel filter is used. The fuel filter is shown in Figure 12. A three stage filter including zeolite crystals therein of the synthetic 25M (Mobil) types or the natural types. Typically a zeolite acts as a molecular sieve. The zeolite crystals are used to filter the methanol to remove any
20 hydrocarbon impurities therefrom. These zeolites can include a set of layers of three or more with pore sizes varying from 3-10Å gradually from layer 1-3

1 2 3 CH₃OH, H₂O, O₂, H₂

Layer 1 is typically the large pore diameter zeolite X, offerite, A to remove large molecules. Mordenite, a natural zeolite, is used in layer 2 to exclude n-paraffins, n-
5 butanes and n-alkanes. Zeolite 3A or 4A can be used to remove small molecules such as propane and ethane in layer 3. This preferably forms a graded molecular sieve.

Mono-polar approaches.

Previous approaches to fuel cells used a number of
10 fuel cells in series. The series connection of fuel cells adds the output voltages to form a higher overall allowed the output of the stack to be increased to a higher and more usable voltage. The inventor of the present invention realized, moreover, certain advantages which can be obtained
15 from using a non stacked approach, which the present inventor has labelled mono-polar. This monopolar approach maintains each membrane electrode assembly completely separately from all the others. This completely different approach allows each element of the assembly to be made much
20 larger, and with a better efficiency. However, we can only get a lower output voltage. Each mono-polar element can be

assembled into a stack. The important thing according to this feature is that each membrane electrode assembly is separately connected, and the separately connected elements are connected in series, rather than assembling them into a
5 stack.

A first embodiment of the monopolar invention is shown in Figure 13. This embodiment could be used to form a fuel cell that does not require contact forces in order to make electrical connections. Membrane 1300 is preferably a
10 Nafion membrane. The Nafion membrane includes a central area with a termination of metal cloth strips 1302, eg a screen. The metal cloth or screen 1302 is covered with appropriate catalysts of the types described above. Current carrying tabs 1304 bring the voltage which is produced to
15 the outside.

A plastic or metal flow field insert 1306 channels the appropriate fuel material to the respective side of the catalyst-covered cloth. Flow field element 1308 can be located on the other side.

20 The material with the catalyst thereon is therefore attached to the Nafion backing and pressed thereagainst to

form a fuel cell in a similar electrical but different mechanical way.

Figure 14 shows a cross-section of the device. The tabs 1304 conduct the electricity to an electrode area 1400. Methanol is brought into a methanol chamber 1402, into a sealed area on a first side of the membrane. The seal is maintained by a ring sealing area 1406. Air is conducted to a second side of the membrane through air chamber 1408, which is similarly sealed on the other side. Each of these elements operates as a stand-alone unit, independent of the other units. The current from these elements can be connected in series to provide a higher voltage.

A second alternative embodiment of the invention is shown in Figure 15. This embodiment uses a membrane 1500, along with a titanium sheet 1502. Titanium cloth 1504 is spot-welded to the titanium sheet. The titanium cloth 1504 acts as the cathode and may be coated with platinum. Titanium cloth 1506 acts as the anode and may be coated with appropriate platinum ruthenium.

A gasket and bonding ring 1508 forms a chamber 1510 between the membrane and the anode. In a similar way,

another gasket and bonding ring 1510 forms a chamber between the membrane and the cathode.

The titanium sheet has a bead seal 1512 thereon to maintain the chamber. Voltage produced by the titanium
5 sheet is coupled to the current takeoff area 1514.

This embodiment also includes places for rivets or fasteners, since the bead sealing would allow metal fasteners to be used. This integrated system could be extremely thin, especially if titanium foil were used.

10 The elements could be used in a device shown in Figure 16. Each of these dual cell modules shown in Figures 13 or 15 includes a cathode and anode thereon. The elements shown in Figure 16 are assembled to form two adjacent anodes up to cells 1602 and 1604 which face one another. A flow
15 field 1606 is established between the anode 1602 and 1604. This flow field should include an air flow there between. In a similar way, two adjacent cathode face one another and a flow field 1608 is formed therebetween to include the appropriate airflow therebetween.

20 Figure 17 shows an expanded view of how these cells would be used. Flow field 1700 is an airflow field which faces the cathode side 1702 of first cell 1704. The anode

side 1706 faces a second, methanol flow field 1708.

Methanol is input through methanol input port 1710 and out through output port 1712. The methanol flow field also faces the anode side 1714 of a second bipolar cell 1716.

5 The cathode side 1720 of the second bipolar cell 1716 faces another flow field element 1722 for air.

Although only a few embodiments have been described in detail above, those having ordinary skill in the art will certainly understand that many modifications are possible in
10 the preferred embodiment without departing from the teachings thereof.

All such modifications are intended to be encompassed within the following claims. .

What is claimed is:

1. A fuel cell element of a type intended for an electrochemical reaction, comprising: a backing, and a catalytic material, including uniformly mixed and randomly spaced platinum-ruthenium bimetallic powder which has
5 distinct sites of platinum and ruthenium.

2 . An element as in claim 1 wherein said material is sufficiently homogeneous that it appears all grey under a scanning electron microscope.

10 3. A method of forming a material for a fuel cell element, comprising:

forming a solution of platinum, ruthenium, and an extra material which maintains a separation between the platinum and the ruthenium,

15 mixing said solution;

processing said solution, said processing including at least heating said solution; and

after said processing, further operating on said solution in a way to remove the extra material.

4. Method as in claim 3, wherein said extra material includes chlorides, and said further operating includes washing the material.

5. Method as in claim 4. wherein said forming a
5 solution comprises forming a slurry of platinum salts and ruthenium salts in hydrochloric acid, said slurry including a chloroplatinic acid hexahydrate salt and a ruthenium salt $K_2RuCl_6 \cdot H_2O$, and stirring said slurry to obtain a homogeneous mixture.

10 6. A method as in claim 3, wherein said forming a solution further comprises adding sodium carbonate while maintaining a specified pH.

7. A method as in claim 3, further comprising replacing at least some of the ruthenium with a material
15 that has characteristics like ruthenium.

8. A method as in claim 7, wherein said material that has characteristics like ruthenium is one of iridium, titanium, osmium, chromium and/or Manganese.

9. A method as in claim 3, further comprising replacing at least some of the platinum with a material that has characteristics like platinum.

10. A method as in claim 9, wherein said material
5 that has characteristics like platinum is at least one of palladium, tungsten, Rhodium, Iron, Cobalt, and/or Nickel.

11. A fuel cell element of a type intended for an electrochemical reaction, comprising: a backing, and a catalytic material, including catalytic material therein,
10 said catalytic material including a material having characteristics that are similar to platinum and ruthenium.

12. A fuel cell element as in claim 11, wherein said material that has characteristics like ruthenium is one of iridium, titanium, osmium, chromium and/or Manganese.

15 13. A fuel cell element of a type intended for an electrochemical reaction, comprising: a backing, and a catalytic material, including catalytic material therein,

said catalytic material including a material having characteristics that are similar to platinum.

14. A fuel cell element as in claim 13, wherein said material that has characteristics like platinum is at least one of palladium, tungsten, Rhodium, Iron, Cobalt, and/or Nickel.

15. A fuel cell electrode comprising,
a backing material, including Teflon particles embedded therein, and
catalytic materials coated on said backing material.

16. A fuel cell electrode as in claim 15, wherein said Teflon particles are added in an amount that is effective to render the backing material water repellent, but to prevent the catalytic materials from seeping therethrough.

17. A fuel cell electrode as in claim 16, wherein said Teflon particles comprise a specified weight percentage of the backing material.

18. A method of forming a fuel cell electrode,
5 comprising:

obtaining a backing material;

treating said backing material with a waterproofing solution, while limiting an amount of waterproofing impregnation into the material, said limiting treating said
10 material in an amount effective to render the material wettable but not porous.

19. A method as in claim 18, wherein said backing material is carbon paper, and said waterproofing solution is Teflon.

15 20. A method as in claim 19, wherein said treating comprises:

forming a Teflon solution, and

dipping the carbon paper into the Teflon solution while making minimal contact with any surface of the carbon paper.

21. A method as in claim 20, wherein said dipping
5 comprises holding the carbon paper with Teflon coated tweezers.

22. A method as in claim 19, further comprising drying the treated carbon paper backing.

23. A method as in claim 18, wherein said drying
10 comprises laying the backing material across supports.

24. A method as in claim 23, wherein said supports are Teflon coated wires with kinks therein.

25. A method as in claim 22, further comprising weighing the dried paper, and determining if sufficient
15 Teflon has been added from an amount of weight gain of the dried paper relative to an original weight of the paper.

26. A method of forming a fuel cell comprising:
obtaining catalyst materials;
mixing said catalyst materials with an ionomer and
with a water repelling material to form a mixed catalyst
5 material; and
applying the mixed material to an electrode backing
material.

27. A method as in claim 26, wherein said mixing
comprises first mixing the catalyst materials with the water
10 repelling material, and then adding the ionomer.

28. A method as in claim 27, wherein water
repelling material is Teflon, and said ionomer is liquid
nafion.

29. A method of forming a porous electrode for a
15 fuel cell, comprising:

sputtering a mixture of a first catalyst material
and a second material onto a backing to form a combined
sputtered material of said first material and said second
material; and

washing away said second material using a washing element that does not remove said first material, to leave said first material with pores therebetween.

30. A method as in claim 29 wherein said second
5 material is an aluminum material, and said washing technique uses KOH to remove said aluminum material.

31. A method as in claim 30, wherein said first material is a platinum-containing material.

32. A membrane electrode assembly, comprising
10 an anode electrode including a fuel cell catalyst material thereon, a proton conducting solid electrolyte member, and a cathode electrode including an appropriate fuel cell catalyst, all press bonded to one another in that order so that said electrolyte member is between said anode
15 and cathode electrodes.

33. A membrane electrode assembly as in claim 32, wherein said anode, electrolyte and cathode are all wet materials.

34. A method of forming a membrane electrode assembly, comprising:

forming a stack including an anode electrode that has an appropriate fuel cell catalyst thereon, a proton
5 conducting solid electrolyte member, and a cathode electrode including an appropriate fuel cell catalyst thereon; and

heating and pressing the stack by an amount which is effective to bond the materials into a bonded membrane electrode assembly.

10 35. A method as in claim 34, wherein said heating and pressing comprises:

first pressing the stack between elements of a pressing machine,

then, some time after said first pressing, heating
15 the stack while maintaining pressure thereon by said pressing,

and then, some time after said heating under pressure, cooling the stack while maintaining the pressure.

36. A method as in claim 35, wherein said first
20 pressing comprises pressing the materials to between 1000

and 1500 psi, said heating comprises increasing the heat to 140 - 150 ° C.

37. A fuel cell comprising:

at least anode and cathode electrodes;

5 a fuel supply conduit; and

a flow field element, operating to supply fuel from said fuel supply conduit to at least one of said anode and cathode electrodes, said flow field element being pressed against said one electrode, and comprising a plurality of 10 island areas, each having a pressing surface having a top surface and side surfaces, the pressing surfaces pressed against said one electrode, and said a flow field area surrounding said side areas, said flow field in communication with said fuel supply conduit,

15 wherein said fuel supply conduit includes at least one opening to the flow field which extends in a direction and supplies the fuel to the flow field in said direction, said direction supplying the fuel directly to one of said side surfaces.

38. A fuel cell as in claim 37, wherein said island areas are rectangular, and have a long axis which is parallel to said direction, and said fuel is supplied to one of said side surfaces which extends perpendicular to said
5 direction.

39. A fuel cell as in claim 38, wherein said fuel supply conduit includes a plurality of nozzles, all extending in said direction and all supplying fuel against one of said side surfaces.


10 40. A method of supplying fuel to an electrode of a type that requires pressure thereagainst, comprising:

pressing a flow field element against the electrode, said flow field element comprising a plurality of island areas, each having a pressing surface having a top surface
15 and side surfaces, the pressing surface top surface pressed against said one electrode, and said flow field area surrounding said side areas

communicating said flow field with said fuel supply conduit in a way to supply the fuel to said side surface of
20 one of said flow field element

1/11

FIG. 1






FIG. 2




FIGURE 3

4/11




FIGURE 4

5/11




FIGURE 5

6/11




FIGURE 6

7/11

BIPLATE REQUIREMENTS FOR DIRECT METHANOL FUEL CELL




FIGURE 7

CONCEPT OF A LAYERED TITANIUM/CARBON ULTRATHIN BIPLATE
FOR FUEL CELLS





FIGURE 8

Fuel Storage Tanks



Direct Methanol Liquid Feed Fuel Cell

FIGURE 9

10/11




FIGURE 10




FIGURE 11

11/11




FIGURE 12

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US96/19731

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :H01M 4/92, 8/10

US CL :429/30, 42; 502/101

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 429/30, 39, 42; 427/115; 502/101

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

ORBIT Derwent World Patent Index

Search Terms: pt, platinum, ru, ruthenium, I03-e04b/mc (Derwent Manual Code for fuel cell electrodes)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,225,391 A (STONEHART et al) 06 July 1993, col. 2, lines 7-25.	11-14
X	US 5,294,580 A (DUFNER) 15 March 1994, col. 2, lines 15-46.	11-14
X	US 5,013,618 A (LUCZAK) 07 May 1991, col. 2, lines 13-39.	11-14
X	US 4,350,608 A (GESTAUT) 21 September 1982, col. 6, lines 11-21, col. 9, lines 8-11.	15-17
X	US 5,294,232 A (SAKAIRI et al) 15 March 1994, col. 4, lines 12-29.	32-34
X	US 4,766,043 A (SHIROGAMI et al) 23 August 1988, fig. 2, col. 3, line 67-col. 4, line 16.	37-40

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"A" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

10 MARCH 1997

Date of mailing of the international search report

25 APR 1997

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

STEPHEN J. KALAFUT

Telephone No. (703) 308-0433

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US96/19731

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4,395,322 A (HARRIS) 26 July 1983, col. 1, lines 34-46.	29-31
A	US 5,415,888 A (BANERJEE et al) 16 May 1995, col. 4, lines 36-58.	18-28
A, P	US 5,561,000 A (DIRVEN et al) 01 October 1996, col. 2, lines 45-60.	18-28
X	JP 2-51,865 A (MATSUSHITA) 21 February 1990, abstract, lines 1-8.	1-2

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.